



TORQU3® 5W30 API SP, ILSAC GF-6A SEMI SYNTHETIC

(Premium Quality, Multigrade, High Performance Engine Oils)

Developed using cutting edge technology from USA, a premium blend using high end synthetic and selected mineral base stocks together with the best top-tier additives available today. TORQU3® 5W-30 API SP SEMI SYNTHETIC has developed a medium lower viscosity lubricant that gives excellent throttle response, good fuel efficiency and excellent cleaning performance that keeps your vehicle running like new day after day. While the advanced formulation helps rejuvenate tired engines.

PERFORMANCE BENEFITS

PREMIUM SEMI-SYNTHETIC FORMULATION

- High percentage of fully synthetic base stocks leads to advanced thermal stability to withstand high oxidative stress leading to a longer drain interval. Excellent general lubrication.

ADVANCED ADDITIVE PACKAGE API SP

- Designed to protect against low-speed pre-ignition and timing chain wear in gasoline direct injection (GDI) engines. Improved sludge and varnish control coupled with improved high temperature deposit protection for pistons and turbochargers. Meets resource conserving ILSAC GF-6A combining increased fuel efficiency and better emissions control.

MEDIUM LOW VISCOSITY LOW FRICTION

- Increased fuel efficiency over higher viscosity oils, excellent throttle response.

PREMIUM MULTIGRADE

- Stable viscosity over varying temperatures enhances lubrication protection over a wider temperature range.

MEETS SPECIFICATIONS & APPROVALS

- API SP
- ILSAC GF-6A
- Ford WSS-M2C946-A
- Ford WSS-M2C946-B1
- FORD WSS-M2C961-A1
- API CF

RECOMMENDATIONS

API SP

- Optimized for gasoline. Recommended where SAE 10W-30 and API SP is required. Meets API SP and superseeds previous categories.

Protect the Environment

Dispose of used oils responsibly. Do not discharge into drains, soil or water.

TORQU3® 5W30 API SP ILSAC GF-6A SEMI SYNTHETIC

SAE Viscosity Grade		5W-30
Kinematic viscosity at 40°C (cSt)	ASTM D445	63
Kinematic viscosity at 100°C (cSt)	ASTM D445	10.3
Density at 15°C	ASTM D4052	0.8581
Flash point, °C	ASTM D92	220
Pour point, °C	ASTM D97	-40
Viscosity Index	ASTM D2270	152

These characteristics are typical of current production. Whilst future production will conform to TORQU3's specification, variations in these characteristics may occur.

